



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : C21D 9/04, 1/20, 1/02, C22C 38/00		A1	(11) International Publication Number: WO 96/22396
			(43) International Publication Date: 25 July 1996 (25.07.96)
(21) International Application Number: PCT/GB96/00034		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 11 January 1996 (11.01.96)		<p><b>Published</b></p> <p><i>With international search report.</i></p> <p><i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
(30) Priority Data: 9501097.1 20 January 1995 (20.01.95) GB			
(71) Applicant (for all designated States except US): BRITISH STEEL PLC [GB/GB]; 9 Albert Embankment, London SE1 7EN (GB).			
(72) Inventors; and (75) Inventors/Applicants (for US only): BHADESHIA, Harshad, Kumar, Dharamshi, Hansraj [GB/GB]; 57 Barrons Way, Camberton, Cambridge CB3 7EQ (GB). JERATH, Vijay [GB/GB]; 26 Heron Hill, Aston, Sheffield, South Yorkshire S31 0GF (GB).			
(74) Agents: FRY, Alan, Valentine et al.; Fry Heath & Spence, The Old College, 53 High Street, Horley, Surrey RH6 7BN (GB).			
(54) Title: IMPROVEMENTS IN AND RELATING TO CARBIDE-FREE BAINITIC STEELS AND METHODS OF PRODUCING SUCH STEELS			
(57) Abstract			
<p>A method of producing a wear and rolling contact fatigue resistant bainitic steel product whose microstructure is essentially carbide-free. The method comprises the steps of hot rolling a steel whose composition by weight includes from 0.05 to 0.50 % carbon, from 1.00 to 3.00 % silicon and/or aluminium, from 0.50 to 2.50 % manganese, and from 0.25 to 2.50 % chromium, balance iron and incidental impurities, and continuously cooling the steel from its rolling temperature naturally in air or by accelerated cooling.</p>			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

Improvements in and relating to Carbide-Free Bainitic  
Steels and Methods of producing such Steels

This invention relates to carbide-free bainitic steels and to methods of producing such steels. More especially, but not exclusively, the invention relates to carbide-free bainitic steels having enhanced wear resistance and rolling contact fatigue from which *inter alia* track and crane rails, railway points and crossings, railway wheels and special abrasive wear resistant sections and plates can be produced.

Most track rails have hitherto been produced from pearlitic steels. Recent reviews have indicated that pearlitic steels are approaching the limit of their material property development for track rails. There is therefore a need to evaluate alternative types of steel having good wear and rolling contact fatigue resistance coupled with improved levels of ductility toughness and weldability.

EP 0612852A1 discloses a process for manufacturing high-strength bainitic steel rails having good rolling-

contact fatigue resistance in which the head of the hot-rolled rail is subjected to a discontinuous cooling programme which entails accelerated cooling from the austenite region to a cooling stop temperature of 500 to 300°C at a rate of 1° to 10°C per second, and then cooling the rail head further to a still lower temperature zone. Rails produced by this process were found to wear away more readily than conventional pearlitic rails and exhibited an improved resistance to rolling-contact fatigue. Thus, the increase in wear rate exhibited by the head surfaces of these rails ensured that accumulated fatigue damage wore away before defects occurred. The physical properties exhibited by these rails are achieved in part by the accelerated cooling regime referred to above.

The solution proposed by EP 0612852A1 differs markedly to the method of the present invention which achieves in rail steels substantially enhanced wear resistance with excellent resistance to rolling-contact fatigue. These steels also show improved impact toughness and ductility in comparison with pearlitic rails. The method of the present invention also avoids the need for a complicated discontinuous cooling regime as specified in EP 0612852A1.

Other similar documents specifying complicated discontinuous cooling regimes include GB 2132225, GB 207144, GB 1450355, GB 1417330, US 5108518 and EP 0033600.

Track rails produced from iron carbide containing bainitic steels have been proposed previously. Whereas the fine ferrite lath size (-0.2-0.8  $\mu\text{m}$  wide) and high

dislocation density of continuously cooled bainite combine to make the steels very strong, the presence in the microstructure of inter and intralath carbides leads to increased embrittlement which has to a large extent tended to hinder commercial exploitation of such steels.

It is known that the embrittlement problem which occurs because of the presence of deleterious carbides can be largely alleviated by employing relatively large silicon and/or aluminium additions (~1-2%) to low-alloy steels. The presence of silicon and/or aluminium in steels continuously transformed to bainite encourages the retention of ductile high carbon austenite regions in preference to the formation of brittle intralath cementite films, and depends on the premise that the dispersed, retained austenite should be both thermally and mechanically stable. It has been shown that the retained austenite following continuous cooling transformation in the bainitic temperature range occurs either as finely divided thin intralath films, or in the form of "blocky" interpacket regions. While the thin film morphology has extremely high thermal and mechanical stability, the blocky type can transform to high carbon martensite, less conducive to good fracture toughness. A ratio of thin film to blocky morphology  $>0.9$  is required to ensure good toughness, and this can be achieved through a careful choice of steel composition and heat treatment. This results in an essentially carbide free, "upper bainite" type microstructure based on bainitic ferrite, residual

austenite and high carbon martensite.

It is an object of the present invention to provide carbide-free bainitic steels with substantially enhanced ranges of hardness, and which exhibit clear advantages over known track rail steels.

According to the present invention in one aspect there is provided a method of producing a wear and rolling contact fatigue resistant bainitic steel product whose microstructure is essentially carbide-free, the method comprising the steps of hot rolling a steel whose composition by weight includes from 0.05 to 0.50% carbon, from 1.00 to 3.00% silicon and/or aluminium, from 0.50 to 2.50% manganese, and from 0.25 to 2.50% chromium, balance iron and incidental impurities, and continuously cooling the steel from its rolling temperature naturally in air or by continuously accelerated cooling.

The steel may additionally include one or more of the following by weight:- up to 3.00% nickel; up to 0.025% sulphur; up to 1.00% tungsten; up to 1.00% molybdenum; up to 3% copper; up to 0.10% titanium; up to 0.50% vanadium; and up to 0.005% boron.

The carbon content of preferred steel compositions may be from 0.10 to 0.35% by weight. The silicon content may be from 1.00 to 2.50% by weight. Also the manganese content may be from 1.00% to 2.50% by weight, the chromium content may be between 0.35 and 2.25% by weight and the molybdenum content may be from 0.15 to 0.60% by weight.

In another aspect, the invention provides a wear and

rolling contact fatigue resistant steel produced by the processes specified in the preceding three paragraphs.

In a still further aspect, there is provided a hot rolled or enhanced cooled rolling contact fatigue and wear resistant bainitic steel rail having an iron carbide-free microstructure, the rail, after hot rolling, having been cooled continuously naturally in air or by accelerated cooling.

Steels in accordance with the invention exhibit improved levels of rolling contact fatigue strength, ductility, bending fatigue life and fracture toughness, coupled with rolling contact wear resistance similar to or better than those of the current heat treated pearlitic rails.

Under certain circumstances it is considered advantageous for the rail to possess an adequately high wear rate in order to allow the accumulated rolling contact fatigue damage on the surface of the rail head to be continually worn away. One obvious way to increase the wear rate of the rail is by decreasing its hardness. A significant reduction in the hardness of the rail, however, causes severe plastic deformation to occur on the surface of the rail head, which in itself is undesirable.

The novel solution to this problem lies, therefore, in being able to produce a sufficiently high hardness/strength rail to resist excessive plastic deformation during service, thereby maintaining the desired rail shape, yet possessing a reasonably high wear rate for continual

rolling contact fatigue damage removal. This has been achieved in the present invention by the deliberate introduction in the essentially carbide free bainitic microstructure of a small proportion of soft pro-eutectoid ferrite, through an appropriate adjustment to the steel composition.

One processing advantage of the natural air cooled bainitic steels in accordance with the invention over the current high strength pearlitic steel rails lies in the elimination of heat treatment operations during both the production of the rail and its subsequent joining by welding.

The invention will now be described by way of example only with reference to the accompanying diagrammatic drawings which:-

Figure 1 illustrates a hardness profile of an iron carbide-free bainitic steel rail in accordance with the invention;

Figure 2 is a schematic CCT diagram for a carbide-free bainitic steel in accordance with the invention;

Figure 3 is a scanning electron micrograph for a carbide-free bainitic steel in accordance with the invention;

Figure 4 show Charpy V-notch impact transition curves for, as-rolled, iron carbide-free bainitic steel in accordance with the invention compared with similar curves for plain carbon heat treated pearlitic steel used currently in railway track;



Figure 5 is a graph of laboratory rolling contact wear rate against hardness of steel samples produced from carbide-free bainitic steels in accordance with the invention;

Figure 6 illustrates abrasive wear lives of carbide-free bainitic steels in accordance with the invention and commercially available wear resistant materials against rounded quartz abrasive;

Figure 7 is a graph showing a hardness profile of flash butt welded carbide-free bainitic steel plate in accordance with the invention; and

Figure 8 is a jominy hardenability curve for as-rolled carbide-free bainitic steel in accordance with the invention.

A primary objective of the present invention is to provide a high strength wear and rolling contact fatigue resistant microstructure comprising primarily carbide free "bainite" with some high carbon martensite and retained austenite in the head of the rail. In practice, it has been found that this high strength microstructure is also present in both the rail web and foot regions of the as-rolled rail. A typical Brinell hardness (HB) profile for a 113 lb/yd rail section is shown in Figure 1.

The high strength head, web and foot regions of the rail provide good rolling contact and bending fatigue performance during service in track.

This and other desired objectives are achieved by careful selection of the steel composition and by either

continuously cooling the steel in air or accelerated cooling after hot rolling.

Composition ranges for steels in accordance with this invention are set out in Table A below.

TABLE A

Element	Composition Range (wt%)
Carbon	0.05 to 0.50
Aluminium/Silicon	0.50 to 3.0
Manganese	0.05 to 2.5
Nickel/Copper	up to 3.0
Chromium	0.25 to 2.5
Tungsten	up to 1.0
Molybdenum	up to 1.00
Titanium	up to 0.10
Vanadium	up to 0.50
Boron	up to .0050
Balance	Iron & Incidental Impurities

Within the ranges, variations may be made depending on, *inter alia*, the hardness, ductility etc. required. All steels are however essentially bainitic in nature and are carbide free. Thus, the preferred carbon content may fall within the range 0.10 to 0.35% by weight. Also, the silicon content may be from 1 to 2.5% by weight, the manganese content from 1 to 2.5% by weight, the chromium content from 0.35 to 2.25% by weight and the molybdenum content from 0.15 to 0.60% by weight.

Steels in accordance with the invention generally exhibit hardness values of between 390 and 500 Hv30, although it is also possible to produce steels with lower

hardness levels. Typical hardness values, wear rates, elongation and other physical parameters can be seen from Table B appended hereto which identifies eleven sample steels in accordance with the invention.

Figure 2 shows a schematic CTT diagram. The addition of boron serves to retard the transformation to ferrite, such that during continuous cooling, bainite forms over a wide range of cooling rates. In addition, the bainite curve has a flat top so that the transformation temperature is virtually constant over a wide range of cooling rates, resulting in only small variations in strength across relatively large, air cooled or accelerated cooled sections.

The steels listed in Table B were rolled to 30 mm thick plates (cooling rates of 30 mm thick plate are close to those at the centre of a rail head), from 125 mm square ingots, and normal air cooled from a finish rolling temperature of 1000°C to ambient temperature. The as-rolled microstructures thereby developed comprise essentially a mixture of carbide free bainite, retained austenite with varying proportions of high carbon martensite as illustrated in Figure 3.

A comparison of the range of mechanical properties achieved in the as-rolled, 30 mm thick experimental bainitic steel plates with those obtained typically for currently produced mill heat treated rails (MHT) is given below:-

**SUBSTITUTE SHEET (RULE 26)**

Rail type	0.2%PS (N/mm <sup>2</sup> )	TS (N/mm <sup>2</sup> )	El (%)	RoFA (%)	HV30	CVN(J) at 20°C	K <sub>IC</sub> at -20°C MPcm <sup>1/2</sup>	Wear Rate, mg/m of Slip (contact stress 750 N/mm <sup>2</sup> )
MHT	800- 900	1150- 1300	9- 13	20-25	360- 400	3-5	30-40	20-30
Bainitic	730- 1230	1250- 1600	14- 17	40-55	400- 500	20-39	45-60	3-36

The properties of the as-rolled, 30mm thick, bainitic steel plates represent a significant increase in strength and hardness levels compared with those of the heat treated pearlitic rail, accompanied by an improvement in the Charpy impact energy level from 4 to typically 35J at 20°C. Charpy V-notch impact transition curves for two of the as-rolled bainitic rail steel compositions (0.22%C, 2%Cr, 0.5%Mo, B free and 0.24%C, 0.5% Cr, 0.5%Mo and 0.0025%B) together with a plain carbon, mill heat treated, pearlitic rail, are shown in Figure 4. The two bainitic rail steels can also be seen to retain high impact toughness down to temperatures as low as -60°C.

The laboratory rolling contact wear performance of the as-rolled, 30 mm thick bainitic steel plates under a contact stress of 750 N/mm<sup>2</sup> was established to be significantly better than that of the current pearlitic heat treated rails, as illustrated graphically in Figure 5.

Tests carried out in relation to steels in accordance with the invention have also shown the bainitic steel compositions to offer a high resistance to wear under abrasive conditions, with relative wear lives of around 5.0

in comparison with a mild steel standard, against a rounded quartz aggregate. Figure 6 shows that these wear life values are superior to those of many commercially available wear resisting materials, including Abrazo 450 and a 13%Cr martensitic steel.

The fracture toughness (resistance to the propagation of a pre-existing crack) of the as-rolled 30 mm thick bainitic steel plates has been found to be significantly higher at between 45 and 60 MPam<sup>1/2</sup> in comparison with those of the heat treated pearlitic rails, with typical values in the range 30-40 MPam<sup>1/2</sup>.

The as-rolled, 30 mm thick steel plates were found to be readily flash butt weldable with hardness levels in the critical weld HAZ regions of normal air cooled, flash butt welded plates either matching, or slightly higher than, those of the parent plate material, as shown in Figure 7.

The as-rolled, 30 mm thick experimental bainitic steel plates possessed high hardenabilities as illustrated in Figure 8, with almost constant hardness levels being developed at distances of between 1.5 and 50 mm from the quenched end, corresponding to cooling rates at 700°C of between 225 and 2°C/s.

Whereas the invention has been described with particular reference to rails, other envisaged applications for these steels include crane rails, railway points and crossings (both as-cast and fabricated), railway wheels, special abrasive wear resistant sections and plates, and special structural applications.

CLAIMS


1. A method of producing a wear and rolling contact fatigue resistant bainitic steel product whose microstructure is essentially carbide-free, the method comprising the steps of hot rolling a steel whose composition by weight includes from 0.05 to 0.50% carbon, from 1.00 to 3.00% silicon and/or aluminium, from 0.50 to 2.50% manganese, and from 0.25 to 2.50% chromium, balance iron and incidental impurities, and continuously cooling the steel from its rolling temperature continuously and naturally in air or by accelerated cooling.
2. A method as claimed in claim 1 wherein the steel additionally includes one or more of the following by weight:- up to 3.00% nickel; up to 0.025% sulphur; up to 1.00% tungsten; up to 1.00% molybdenum; up to 3% copper; up to 0.10% titanium; up to 0.50% vanadium; and up to 0.005% boron.
3. A method as claimed in claim 1 or claim 2 wherein the carbon content of the steel is from 0.10 to 0.35% by weight.
4. A method as claimed in any one of the preceding claims wherein the silicon content is from 1.00 to 2.50% by weight.

5. A method as claimed in any one of the preceding claims wherein the manganese content is from 1.00% to 2.50% by weight, the chromium content is between 0.35 and 2.25% by weight and the molybdenum content is from 0.15 to 0.60% by weight.
6. A wear and rolling contact fatigue resistant steel produced by a method as claimed in any one of the preceding claims.
7. A hot rolled or enhanced cooled rolling contact fatigue and wear resistant bainitic steel rail having an iron carbide-free microstructure, the rail, after hot rolling, having been cooled either continuously and naturally in air or accelerated cooled.
8. A bainitic steel whose composition by weight percent comprises the steps of hot rolling a steel whose composition by weight includes from 0.05 to 0.50% carbon, from 1.00 to 3.00% silicon and/or aluminium, from 0.50 to 2.50% manganese, and from 0.25 to 2.50% chromium, balance iron and incidental impurities, and continuously cooling the steel from its rolling temperature naturally in air or by accelerated cooling.
9. A bainitic steel as claimed in claim 8 whose composition additionally includes one or more of the

following by weight:- up to 3.00% nickel; up to 0.025% sulphur; up to 1.00% tungsten; up to 1.00% molybdenum; up to 3% copper; up to 0.10% titanium; up to 0.50% vanadium; and up to 0.005% boron.

10. A bainitic steel whose carbon content is from 0.10% to 0.35% by weight.
11. A bainitic steel whose silicon content is from 1.00% to 2.50% by weight.
12. A bainitic steel whose manganese content is from 1.00% to 2.50% by weight.





**FIG. 1**





FIG. 2

3/8



× 5000

**FIG. 3**

4/8




FIG. 4

5/8





FIG. 5

FIG. 6



7/8




FIG. 7




FIG. 8



# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GB 96/00034

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C21D9/04 C21D1/20 C21D1/02 C22C38/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C21D C22C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 94, no. 011 & JP,A,06 316728 (NIPPON STEEL CORP), 15 November 1994, see abstract	1,7,8
Y	GB,A,1 131 662 (LORRAINE-ESCAUT) 23 October 1968 see claims 1,13	1,7
Y	US,A,3 915 697 (GIULIANI LUCIO ET AL) 28 October 1975 see the whole document	1,7
Y	CH,A,331 618 (OESTERREICHISCH-ALPINE MONTANGESSELLSCHAFT) 15 September 1958 see claims	7
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&\* document member of the same patent family

Date of the actual completion of the international search

3 May 1996

Date of mailing of the international search report

12-05-96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

Mollet, G

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GB 96/00034

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	GB,A,2 182 675 (MAN NUTZFAHRZEUGE GMBH) 20 May 1987 see claims 1,4 ---	7
A	EP,A,0 612 852 (NIPPON STEEL CORP) 31 August 1994 cited in the application ---	
A	DE,B,23 02 865 (FRIED. KRUPP HÜTTENWERKE) 25 July 1974 cited in the application ---	
P,X	STAHL UND EISEN, vol. 115, no. 2, 16 February 1995, pages 93-98, 138, XP000496383 BOER DE H ET AL: "NATURHARTE BAINITISCHE SCHIENEN MIT HOHER ZUGFESTIGKEIT" see the whole document -----	1,7,8

# INTERNATIONAL SEARCH REPORT

Information on patent family members

In International Application No.

PCT/GB 96/00034

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-1131662		BE-A- 680222	03-10-66
		DE-B- 1533982	26-11-70
		FR-E- 98024	21-12-67
		FR-A- 1458157	23-01-67
		LU-A- 50979	27-06-66
		NL-A- 6605705	31-10-66
		OA-A- 1952	04-02-70
		SE-B- 309257	17-03-69
US-A- 3519497	07-07-70		
-----			
US-A-3915697	28-10-75	NONE	
-----			
CH-A-331618		NONE	
-----			
GB-A-2182675	20-05-87	DE-A- 3533493	26-03-87
		DE-A- 3628264	25-02-88
		FR-A- 2588570	17-04-87
		JP-A- 62116719	28-05-87
		SE-A- 8603897	20-03-87
		US-A- 4737202	12-04-88
-----			
EP-A-0612852	31-08-94	JP-A- 6248347	06-09-94
		JP-A- 6330175	29-11-94
		JP-A- 6336613	06-12-94
		JP-A- 6336614	06-12-94
		JP-A- 7034132	03-02-95
		JP-A- 7034133	03-02-95
		AU-B- 663023	21-09-95
		AU-B- 5630494	01-09-94
		BR-A- 9400689	27-09-94
		CA-A- 2116504	27-08-94
		CN-A- 1095421	23-11-94
		US-A- 5382307	17-01-95
-----			
DE-B-2302865	25-07-74	AU-B- 6473074	24-07-75
		CA-A- 1016849	06-09-77
		GB-A- 1450355	22-09-76

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**